

Deposition of tin(II) sulfide thin films by ultrasonic spraypyrolysis: Evidence of sulfur exo-diffusion

M. MESSAOUDI, M.S. Aida, N. Attaf, Bezzi, J. Bougdira et G.Medjahdi

Abstract: Tin Sulfide (SnS) thin films were deposited by ultrasonic spray pyrolysis technique, on glass substrate heated at 280 °C, with different deposition times. The used precursor SnCl₂ and thiourea are dissolved in methanol. X-ray diffraction (XRD) analysis indicates that films are mainly composed with orthorhombic SnS phase at low deposition time. With increasing deposition time, the hexagonal SnS₂ phases become dominant. SnO₂ and metallic Sn phases have been detected with increasing deposition time. Scanning electron microscopy (SEM) observations reveal that films surfaces are rough with the presence of bubbles due to S₂ gas exo-diffusion from the bulk during film growth. A model of S gas formation is presented.

Keywords : Tin Sulfide Thin films Spray pyrolysis